

.SEC

| Ref. | Description |
|-------|---|
| LG403 | M7.5 NORMAL GREY SPECIAL THERMO-CLAY TYPE MORTAR |
| LG413 | M7.5 WATER-REPELLENT GREY SPECIAL THERMO-CLAY TYPE MORTAR |

DESCRIPTION

- Dry mortar for Masonry based on cement (according to RC-08), hydrated lime (CL 90-S UNE-EN 459), washed lime sand of great purity and selected grain size, light aggregates and chemical additives, specific to build brick walls.
- It has the compulsory **CE** marking, by virtue of that stated in Directive 89/106/CE on construction products and in accordance with standard UNE-EN 998-2.



FIELD OF APPLICATION

- Dry mortar specific designed to build brick walls with Termoarquilla® (thermo-clay) type light clay blocks.
- **PREFASEC® WATER-REPELLENT GREY SPECIAL THERMO-CLAY TYPE MORTAR** is recommended for applications requiring low water absorption mortar.

PROPERTIES

- Optimum thermal insulation.
- Great plasticity.
- Excellent adherence.
- Great workability.
- Excellent mechanical strength.
- Water repellency (in the case of water-repellent mortar): reduced water absorption as opposed to that of normal mortar (see technical characteristics).

METHOD OF USE

Support Preparation

- Must be clean from dust, loose particles, plaster, paint remains, grease, etc.
- In the case of porous, very absorbent or dried up pieces or supports, these must be moistened previously, without soaking them, to enable the adherence and correct curing of the mortar.

Product Kneading

- Knead with approximately 17% of water (4 ¼ litres of water per 25 kg sack).
- Knead with a mechanical mixer – recommended – (at low revs) or manually until achieving a homogeneous mass without lumps.
- Leave to settle for 5 minutes before applying.

Product Application

- The product will be spread over the piece with the trowel according to the indications by the light thermo-clay type block.

RECOMMENDATIONS AND PRECAUTIONS

- Application temperature will be between 5 and 30°C.
- It is convenient to moisten the support at temperatures over 20°C.
- Avoid freezing, strong winds and exposing to intense sunlight application.
- Never apply on surfaces with extreme temperatures.
- Must be used mixed exclusively with water. Any other addition (aggregates, additives, etc.) may modify the behaviour and characteristics of the product.

CONSUMPTION

- The consumption will depend on the thickness applied and on the shape and size of the piece placed.

.SEC

SAFETY AND HYGIENE

- This product contains cement. Cement is an irritant to the eyes, respiratory paths and mucous membranes.
- The paste gives a high pH when mixing the product with water. Therefore, it may irritate the skin in the case of prolonged contact, causing lesions to the eyes in the case of projections.
- Avoid contact with the skin and mucous membranes.
- No smoking, eating or drinking in the premises where the product is used.
- Avoid dust dispersion.
- The appropriate individual protection equipment for each case will be used.
- Persons with sensitive skin backgrounds should not handle this product.
- For more information check the file Product Safety Data File.

TECHNICAL CUSTOMER SERVICE

- It is recommended the appropriate product is used for each application in accordance with the Technical File.
- Please check with our Technical Customer Service in the case of any doubt regarding the selection, handling or application of the different products.
- Our Technical Department will deal with and study each case if it were necessary to use a specific product, according to the use, colour, specifications, etc., or for placing special pieces or formats.

SUPPLY

- 25 kg paper sack with plastic film.
- Special pneumatic transport silos, refillable on site by means of tanker trucks.
- Gravity silos with mixer attached at the base, refillable on site by means of tanker trucks.

STORAGE AND CONSERVATION

- The product maintains its characteristics in a dry place protected from freezing, humidity, direct sunlight, etc.:
 - Sack: 12 months.
 - Silo: 3 months



.SEC

TECHNICAL CHARACTERISTICS



BASIC CHARACTERISTICS – CE MARKING EN 998-2

| Specification | Value | Test Method |
|--|---|--|
| Reaction to fire | Clase A1 | Decisión 96/603/CE |
| Chloride content | < 0.1 % | UNE-EN 1015-17 |
| Dry bulk density of hardened mortar | 1650 ± 50 kg/m ³ | UNE-EN 1015-10 |
| Steam permeability | μ 15/35 | UNE-EN 1745 |
| Thermal conductivity (λ _{10, dry}) | 0.75 W/m·K (P=50%) 0.83 W/m·K (P=90%) | UNE-EN 1745 |
| Initial shearing resistance | 0.15 N/mm ² | UNE-EN 998-2 (Anexo C) |
| Compression strength (N/mm ²) | M7.5 (≥ 7.5) | UNE-EN 1015-11 |
| Water absorption | NORMAL ≤ 1.50 kg/m ² ·min ^{0.5} | WATER-REPELLENT ≤ 0.20 kg/m ² ·min ^{0.5} |

OTHER TECHNICAL DATA

| Specification | Value | Test Method |
|--------------------------------|------------|-------------|
| Application temperature | 5°C – 30°C | - |
| Approximate water for kneading | 17% | - |

NOTE:

Dosage and application outside that described in this file will exclude our responsibility regarding the product and its application.

The results stated were obtained in tests performed under standard conditions and may vary in terms of on site installation conditions.

Please contact our Technical Department for more information.

All the product application indications are based on our current experience and knowledge, with the client being responsible for the final study for on site installation.



Customer service: morteros@morteros.masaveu.com

FÁBRICA ASTURIAS:
Pol. Ind. Riaño I, C/ Chopera, 24
33920 Langreo, Asturias, España.
Tfno.: +34 985 678 068
Fax: +34 985 678 039

FÁBRICA LEÓN:
Ctra. León-La Bañeza, km 4,3
24391 Vill. del Carnero, León, España
Tfno.: +34 987 281 299
Fax.: +34 987 281 312

FÁBRICA PONTEVEDRA:
Ctra. Porriño-Salceda, km 2
36475 Porriño, Pontevedra, España.
Tfno.: +34 986 338 443
Fax.: +34 986 337 967

FÁBRICA VALLADOLID:
Ctra. Adanero-Gijón, km 195,5
47610 Zaratán, Valladolid, España.
Tfno.: +34 983 360 119
Fax.: +34 983 362 307

